



www.butcherblock.com

Durakryl 102 (an ultra violet cured coating) is a proprietary formulation which when cured leaves an insert film. The constituents of the cured film have been tested by an independent university laboratory and found to be non-toxic.

Since the film is approximately 95% cured in the manufacturing process with 100% cure within 2 weeks of manufacture only insert film is present on installed tops used as manufactured.

Since butcher block is such a versatile product our tops are used for many applications. We have had our Durakryl 102 tested to see how it reacts to many household and industrial products. The following is a listing of products tested and the results of the testing. The results are listed as passed (no effect), failed (moderate to severe effect) a moderate effect would be a softening of the finish, or discoloration of the finish.

The Wood Welded Company.



Bally Block Company

Post Office Box 188 30 South Seventh Street Bally, PA. 19503 {Telephone} 610-845-7511 {Facsimile} 610-845-3910

Michigan Maple Block Company

Post Office Box 245 1420 Standish Ave. Petoskey, MI. 49770 {Telephone} 231-347-4170 {Facsimile} 800-447-7975



www.butcherblock.com

<u>INDUSTRIAL</u>	<u>RESULT</u>	<u>HOUSEHOLD</u>	<u>RESULT</u>
Glacial Acidic Acid	P	Tap Water	P
Hydrochloric Acid 100%	P	50-50 SD 3A & H2O	P
Nitric Acid 100%	P	Isopropyl Alcohol	P
Sulphuric Acid 100%	P	Non-Oily Nail Polish Remover	P
Chrome Acid	P	Acetone	P
Ammonium Hydroxide	P	Soap Solution	P
Calcium Hypochlorite	P	Household Detergent	P
Sodium Hydroxide	P	Household Ammonia	P
Acetone	P	Tomato Ketchup	P
Amyl acetate	P	Vegetable Oil	P
Aqua Regia	P	Trisodium Phosphate	P
Benzene	P	Fresh Coffee	P
Butyl Alcohol	P	Fresh Tea	P
Ethyl Acetate	P	Fresh Whole Milk	P
Ethyl Alcohol	P	Citric Acid	P
Ethyl Ether	P	Plain Mustard	P
Formaldehyde	P	Distilled Vinegar	P
Hydrogen Peroxide	P	Lipstick (red)	P
Methyl Alcohol	P	Ink Washable Blue	P
M.E.K	P	Grape Juice	P
Kerosene	P	Red Food Dye	P
Phenol	P	Beet Juice	P
Silver Nitrate	P	Merthiolate	P
Tri Chloroethylene	P	Ink Ball Point Blue	P
Xylene	P	Ink Felt Non-Permanent	P
Zinc Chloride	P	Bleach	P
Auto Transmission Fluid	P	Wax Crayon-Black	P



Bally Block Company

Post Office Box 188 30 South Seventh Street Bally, PA. 19503 {Telephone} 610-845-7511 {Facsimile} 610-845-3910

Michigan Maple Block Company

Post Office Box 245 1420 Standish Ave. Petoskey, MI. 49770 {Telephone} 231-347-4170 {Facsimile} 800-447-7975